

ALEXREPAIR-C



Shrinkage Compensated, Polymer modified Cementitious Structure Repair Mortar

Description

ALEXREPAIR-C is two components, polymer modified cementitious repair mortar. Formulated from bonding agent and selected cementitious mix.

Uses

General repair and renovation of decayed, defective or damaged concrete such as:-

- Columns.
- Walls.
- Beams.
- Floors.
- Honeycombed concrete.

Advantages

- Waterproof preventing penetration of water and chemicals for a good substrate protection.
- Easy to use-simple on site addition of water.
- Excellent bond to properly prepare sound concrete.
- Free flowing- eliminates honeycombing in areas of congested reinforcement.

Surface preparation

- Surfaces should be clean, remove loose material, dust.
- Do not apply over oil contaminated concrete.
- Remove all unsound concrete surfaces by chiseling,hammering or by shot blasting.

- Spray all surfaces with water but remove any free standing water.
- Do not apply over dry surface.

Mixing:

Pour most of the liquid component (A) in a mixing container then slowly add the dry powder (B) while continuing to mix the material together.

Mix for 3 to 5 minutes until a smooth, uniform, homogenous mix is achieved.

Standard

Compressive strength

ASTM C109

Flexural strength

ASTM C348

Properties

Compressive strength	7 Days	28N/mm ²
	28 Days	55N/mm ²
Flexural strength	28 Days	11N/mm ²
Bond strength	3 N/mm ² (concrete failure)	
Density:		
component A	1.03 kg/ lit	
component B	1.235 kg/ lit	
component A+B	2.00 kg/ lit	

Guide to application

Application:

ALEXREPAIR-C should be placed in a single continuous operation. Poured material should be introduced slowly to prevent entrapment of air.

It is essential to place the mixed material within 30 minutes of batching.

Curing:

As with all cementitious material, curing is of vital importance to ensure that optimum properties are obtained. Recommended ALEXCURE WB

Coverage:

Yield approximately 15 lit per 30 kg.

Packing:

Is supplied in 30 kg pack,

Guarantee:

All precaution is taken in manufacture of each product to comply with the standard of each material.

The data sheet for each product for information only and may be corrected and no liability is accepted for it.

The results may have variation because the method of their use condition under which they are applied cannot be anticipated.

Technical Service:

For any technical advice for using the **ALEXCHEM** contact the technical office.

Storage:

Store out of direct sunlight, clear of the ground on pallets protected from rain fall.

Protect from extremes of temperatures.

Shelf life:

Up to 12 months if stored in unopened Containers.

Safety precautions:

Avoid contact with eyes, mouth, and skin.

Treat splashes to eyes by water.

Non toxic.

In the event of prolonged irritation seek medical advice.

HEAD OFFICE:

12 Ibn saad,45 Miami ,Alexandria

Tel:03-5885431 Fax:03-5885253

mob: 01155444400

Website : www.alexchem.net

Email : info@alexchem.net

FACTORY:

ElNahda- Amrya -Alexandria

Tel/Fax:03-4770313